



Technical data sheet

Product name: AzureFilm 3D Wood Pine
Date of issue: 06 March 2017

Version: 1.0

Designation of product, preparation and manufacturer

Trade name: AzureFilm Wood Pine 1.75mm or 2.85mm diameter
Use of product: Biodegradable polymer compound suitable for 3D printing. The biobased carbon content is > 75 % (calculated). Contains wood fibers.
Manufacturer: AzureFilm d.o.o.
Orleška cesta 16
6210 Sežana
Phone: + 386 (0)31 718 800
Mail: info@azurefilm.com
Web: www.azurefilm.com

Mechanical properties

Modulus of elasticity	2,900	[MPa]	ISO 527
Tensile strength	47	[MPa]	ISO 527
Tensile strain at tensile strength	5	[%]	ISO 527
Tensile stress at break	38	[MPa]	ISO 527
Tensile strain at break	6.5	[%]	ISO 527
Flexural modulus	2,950	[MPa]	ISO 178
Flexural strain at break	no break	[%]	ISO 178
Flexural stress at 3.5 % strain	64	[MPa]	ISO 178
Notched impact strength (Charpy), RT	4.4	[kJ/m ²]	ISO 179-1/1 eA
Impact Strength (Charpy), RT	21	[kJ/m ²]	ISO 179-1/1 eU

The values listed have been established on standardized test specimens (DIN EN ISO 3167, type A) at standard temperature and humidity conditions.

Physical properties

Melt flow rate (190 °C/2.16 kg)	2.5 - 4.5	[g/10 min]	ISO 1133
Melt volume rate (190 °C/2.16 kg)	2.2 - 4.0	[cm ³ /10 min]	ISO 1133
Melting temperature	> 155	[°C]	ISO 3146-C
Density	n/a	[g/cm ³]	ISO 1183

Printing Recommendations:

Nozzle temperature: 200 – 230 °C
Heated bed: recommended 0-60 °C
Print speed: 30 – 100 mm/s
Build platform: Blue tape, Kapton tape. Recommended: Glass bed + spray 3D Lac 400ml
We recommended also to use nozzle 0,6mm and 0,15 to 0,20mm layer height

Legal notice

The technical information contained on this sheet is furnished without charge or obligation and accepted at the recipient's sole risk. The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since we cannot anticipate all variations in actual end-use conditions, AzureFilm d.o.o. makes no warranties and assumes no liability in connection with any use of this information.