

Material Data Sheet

PLA



General Information

Extruded Polylactic Acid (PLA) for easy 3D printing from renewable resources. This high definition filament conforms to tight diameter and ovality tolerances and enables print details with precision, very good surface and high resolution. Its high quality and resiliency (non-brittleness) avoid unwanted breakages or deformation of the filament on the spool. This odourless material is available in various colours and exhibits excellent colour coverage and batch-to-batch colour consistency. It is industrially compostable.

3D processing method: FFF (Fused Filament Fabrication)

Diameter (mm): 1.75 and 2.85

Form: wound on a spool (app 333/125 m per 1 kg of 1,75/2,85 filament)

Diameter tolerance (mm): $\pm 0,05/0,06$ on 100 % of the 1,75/2,85 filament length

Packaging: packed in a hermetically sealed plastic bag with silica gel

Colours (with RAL code where applicable): Translucent, White (9016), Light Concrete Grey, Elephant Grey, Metallic Grey, Dark Grey (7011), Black (9017), Dark Blue (5002), Light Blue (5015), Light Green (6018), Dark Green (6002), Red (3020), Orange (2008), Yellow (1023), Coral Pink

Physical Properties	Standard	Value	Unit
Density	ISO 1183	1,25	g/cm ³

Thermal Properties	Standard	Value XY (Flat)	Value	Unit
Heat Deflection Temperature	ISO-75-2 (0,45 MPa)	56,7		°C
Vicat Softening Temperature	ISO 306:2023, B/50	55,4		°C
Glass Transition Temperature	DSC (10°C/min)		60,2	°C
Melting Temperature	DSC (10°C/min)		151	°C

Mechanical Properties	Standard	Value XY (Flat)	Value Z (Up)	Unit
Tensile Modulus	ISO 527-2:2012 (1 mm/min)	2.769	2.741	MPa
Tensile Stress at Yield	ISO 527-2:2012 (50 mm/min)	46,5	36,3	MPa
Tensile Stress at Break	ISO 527-2:2012 (50 mm/min)	39,5	34,8	MPa
Elongation at Yield	ISO 527-2:2012 (50 mm/min)	2,1	1,6	%
Elongation at Break	ISO 527-2:2012 (50 mm/min)	6,5	2,9	%
Flexural Modulus	ISO 178:2019 (1 mm/min)	2.744	2.685	MPa
Flexural Strength	ISO 178:2019 (5 mm/min)	74,8	57,4	MPa
Charpy Impact Strength Notched	ISO 179-1:2011 (2,9 m/s; 0,5 J)	3,3 (C)*	2,9 (C)*	kJ/m ²
Hardness	ISO 868:2004	73,4		Shore D

The tests were performed on material in black colour either on filament or 3D printed parts (XY/Flat or Z/Up). **Printing conditions (3D specimens):** Prusa i3MKS3, nozzle: 220 °C, nozzle type: brass, nozzle diameter: 0,4 mm, bed temperature: 60 °C, layer height 0,2 mm, infill: 100 %, active cooling fan: 100 %, perimeter No: 3, printing speed: 45 mm/s, chamber: closed. Printed parts were conditioned. * C = complete break.

Material Data Sheet / PLA

Printing Conditions

Processing Method: FFF (Fused Filament Fabrication)

Drying: Not necessary if packed properly and contact with moisture prevented.

Dry box: n/a

Nozzle Temperature (°C): 210 ± 20

Speed (mm/s): up to 200

Bed temperature (°C): 35 – 60 (depending on the conditions and complexity of the print, bed heating can be turned off).

Compliance

This material is compliant with:

- **REACH:** Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the *Registration, Evaluation, Authorisation and Restriction of Chemicals* (REACH)
- **RoHS 2:** Directive 2011/65/EU

Contact Information

Roffelsen Plastics

Lichttoren 32

5611 BJ Eindhoven

The Netherlands

Europe

Telephone / +31 (0) 492 59 2800

Email / post@roffelsen.com

Website / www.roffelsen3d.com

Disclaimer

This information sheet has been created with the utmost care. Unless indicated otherwise, this sheet is solely intended to provide general information. It should not be relied on for any specific purpose and no representation or warranty is given with regards to its accuracy or completeness.